



Cartonnages d'Anet

Fiche technique Buvar Sordianne MA15N (noir)

Anet, le 09/07/2008.

Structure:

LDPE 25µm (noir)
MULTI-BONDED Airlaid Fluff pulp / EVA Co-polymers / Bonding Fiber - (White) 110 gsm

Laminated product by hot melt technology

Characteristic	Unit	Method	Min	Mean*	Max
Grammage	gsm	M.I.P.1	133	148	163
Absorption	gsm	M.I.A.2	1350		
Thickness	mm	EN 2973		1,52	
Tensile strenght – Dry MD	N/50mm	ISO 9073 - 4	32		
Tensile strenght – Dry CD	N/50mm	ISO 9073 - 4	22		
Elongation at max. force – Dry MD	%	ISO 9073 - 4	10		20
Elongation at max. force – Dry CD	%	ISO 9073 - 4	27		41

*where not specified, tolerance +/- 10%

Law Requirements:

ABSORBING PAD SUITABLE FOR FOOD CONTACT
(REG 1935/2004/CE, DIR 2002/72/CE AND FURTHER AMENDMENTS)

Issued by: Mr. BUDELLI.