



Cartonnages d'Anet

Fiche technique Buvard Sordianne MA50

Anet, le 06/01/2010.

Structure:

HDPE 10µm (White)
MULTI-BONDED Airlaid Fluff pulp / EVA Co-polymers / Bonding Fiber / Super Absorbent Fibers – (White) 180 gsm
Laminated product by hot melt technology

Characteristic	Unit	Method	Min	Mean*	Max
Grammage	gsm	M.I.P.1	188	209	230
Absorption	gsm	M.I.A.2	4500		
Thickness	mm	EN 2973		1,99	
Tensile strenght – Dry MD	N/50mm	ISO 9073 - 4	46		
Tensile strenght – Dry CD	N/50mm	ISO 9073 - 4	32		
Elongation at max. force – Dry MD	%	ISO 9073 - 4	12		26
Elongation at max. force – Dry CD	%	ISO 9073 - 4	24		36

*where not specified, tolerance +/- 10%

Law Requirements:

Absorbing pad suitable for food contact (REG 1935/2004/CE, DIR 2002/72/CE and further amendments).

Issued by: Mr. BUDELLI.