



Fait le jeudi 2 novembre 2017 à Anet

Les Cartonnages d'Anet  
19 rue Hubert Baraine  
28260 Anet France  
Tél. +33(0)2.37.41.94.33  
[info@budelli.fr](mailto:info@budelli.fr)  
<http://budelli.fr/>

N°SIRET: 672 950 201 000 18 Code APE,  
NAF 212B - FR 91 672 950 201

Objet : fiche technique de notre fournisseur (numfour61) de papier siliconé.

Description : one-side siliconized, precoated, bleached natronkraft providing low release forces.

Construction : silicone / precoat / bleached natronkraft.

Colour : white.

Application : self-adhesive materials.

Properties	Standard / Method	Unit	Target Value	Range
Grammage	ISO 536	g/m <sup>2</sup>	139	+/-9
Caliper	ISO 534	µm	141	+/-12
Release Value	MRLA 30 (tesa 7475)	cN/25mm	G00J1: 9	+/-5
Tensile Strength MD	ISO 1924-2	N/15mm	120	min. 105
Tensile Strength CD	ISO 1924-2	N/15mm	67,5	min. 57
Tear Strength MD	ISO 1974	mN	800	min. 680
Tear Strength CD	ISO 1974	mN	900	min. 770

Warranty : Providing correct packaging and storage of the reels we guarantee the specified release values for 6 months after passage of risk.

Disclaimer : Technical data is subject to modification. This specification does not absolve the user from carrying out its own tests, especially with respect to interactions between adhesive and release liner during production and ageing.

Issued / changed : 02.11.2017

Checked / released : BR

TS number : 1708

Revision No. : 0